

401 - 1K NITRO CELLULOSE GLOSS TOPCOAT

Definition

Product Code	FC401
Nature of the product	NITRO CELLULOSE
Family (NFT 36-003)	FAMILY 1 - CLASS 5 A
Use / Destination	1 K NITRO CELLULOSE TOPCOAT FOR : TOYS, WOOD OR METAL FURNITURES, TUBULAR FURNITURE, MACHINE TOOLS, TOOLS, AGRICULTURAL MACHINERIES, INDUSTRIAL VEHICLES ...ETC CAN BE APPLIED ON WOOD
Tints	ALL OPAQUE TINTS
Aspect	SPECULAR GLOSS 85 TO 90% AT 60° ANGLE










Physical data

Viscosity of delivery (NFT 30-014)	130 SEC AFNOR CUP N° 4 AT 20°C
Density (NFT 30-020)	1,000 TO 1,200 FOLLOWING TINT
Solids by weight (NFT 30-084)	50 % (+/-5)
Solids by volume	30 % (+/-5)
Theoretical coverage	8 TO 10 M ² / L FOR 50 TO 65μ DRY
V.O.C. level	> 420 GR/L

Delivery data

Packaging	1 KG - 5 KG - 25 KG
Flash point	> 23°C
Transportation code	CLASS 3, GROUP 3.3, UN : 1263, IMDG : 3372

This data sheet is designed to inform our customers about the properties of the product. As we can't control the application it is up to the users to make tests to check if the product fits the application. These indicative information are given as objectively as possible and in no case they would involved our responsibility. This data sheet cancels and replaces any anterior edition. MSDS are given on demand.

Use																	
	Substrate CLEANING / SANDING : P 380 – P 400 DRY																
	Preparation SPRAY GUN : <input type="checkbox"/> TOPCOAT 301 : 100 PARTS <input type="checkbox"/> THINNER CL 102 : 20 PARTS <input type="checkbox"/> IN CASE OF HIGH TEMPERATURE USE RETARDER THINNER AT 4% <input type="checkbox"/>																
	Viscosity of application 22 TO 28 SEC AFNOR CUP N°4 AT 20°C																
	Application / Adjustment <table><tr><td></td><td>Nozzle (mm)</td><td>Pressure (bar)</td><td>Number of coats</td></tr><tr><td>Pneumatic</td><td>1 - 1.5</td><td>3.5 - 5</td><td>1 - 2</td></tr><tr><td>Membrane pump</td><td>1 - 1.2</td><td>0.5 - 0.8</td><td>1 - 2</td></tr><tr><td>HVLP</td><td>1.2</td><td>2.0</td><td>1 - 2</td></tr></table>		Nozzle (mm)	Pressure (bar)	Number of coats	Pneumatic	1 - 1.5	3.5 - 5	1 - 2	Membrane pump	1 - 1.2	0.5 - 0.8	1 - 2	HVLP	1.2	2.0	1 - 2
	Nozzle (mm)	Pressure (bar)	Number of coats														
Pneumatic	1 - 1.5	3.5 - 5	1 - 2														
Membrane pump	1 - 1.2	0.5 - 0.8	1 - 2														
HVLP	1.2	2.0	1 - 2														
	Thickness DRY : 40 TO 55μ <input type="checkbox"/> WET : 100 TO 130μ <input type="checkbox"/>																
	Flash off time 10 MIN AT 20°C																
	Drying time DUST FREE : 15 MIN AT 20°C <input type="checkbox"/> DRY TO TOUCH : 30 TO 45 MIN AT 20°C <input type="checkbox"/>																
 	Keeping STORAGE : 2 YEARS IN A SEALED CAN OF ORIGIN STORED BETWEEN 10 AND 30°C																

This data sheet is designed to inform our customers about the properties of the product. As we can't control the application it is up to the users to make tests to check if the product fits the application. These indicative information are given as objectively as possible and in no case they would involved our responsibility. This data sheet cancels and replaces any anterior edition. MSDS are given on demand.